


## 022 Masking tape 80 °C



### Tape structure:

Backing: saturated crepe paper

Adhesive: solvent borne rubber / resins adhesive

### Characteristics:

Masking tape suitable for any painting in building, construction and industrial contexts, and also for automotive applications in the bodyshops with temperatures up to 80 °C.

**Application fields:** building, automotive, aerospace, marine

### Technical features:

indoor, multiple surfaces, no residual, all paints

### Strengths:

- Resistance for 80 °C (60 min), 90 °C (30 min)
- No residue
- Adaptable to irregular surfaces
- Compatible with solvent and water base paint
- Removal without breaking

### Technical information:

Properties	Spec.	Tolerance	Test Method
Total Weight	92 g/m <sup>2</sup>	± 8 %	ISO 536
Total Thickness	125 µm	± 10 %	AFERA 5006
MD Tensile strength	> 28 N/cm		AFERA 5004
MD Elongation at break	> 8 %		AFERA 5004
Adhesion to steel plate	> 2 N/cm		AFERA 5001
Temperature resistance	80 °C (60 min)		

### Available colour:

yellow

### Storage details:

- We recommend a storage temperature between 15 and 25 °C
- The product should not be directly exposed to heat or humidity
- The product should be conditioned to room temperature before use

### Shelf life:

12 months when stored in original carton at 23 °C and max. 50 % relative humidity

### Remark:

Above figures are for reference and cannot be treated as warranties. Customers are advised to test the material to determine the suitability against intended applications.

### IMPORTANT NOTICE TO PURCHASER

All statements technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed and the following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential, arising out of the use of or the inability to use the product. Before using, users shall determine the suitability of the product for their intended use, and assume all risk and liability whatsoever in connection therewith. No statement or recommendation not contained herein shall have any force or effect unless in an agreement signed by officers of seller and manufacture.