





Te

Application fields:

Technical features:

Strengths:

0220 Masking tape 90 °C

Tape structure:

Backing: saturated crepe paper Adhesive: solvent borne rubber / resins adhesive

Characteristics:

Crepe paper masking tape with high performance, specific for automotive sector during collision repairs and painting processes with drying cycles at high temperatures up to 110 °C (for 30 min). It combines controlled unwinding, easy tear and conformability. Well performing in overlapping the tape, with masking paper and masking film, it provides excellent paint edges, clean and safe removal without residues and breakings.

automotive, aerospace, marine

multiple surfaces, no residual, high performance, all paints

- Resistance for 90 °C (60 min) 110 °C (30 min)
- Suitable for all paints
- High performances
- No residue
- Adaptable to irregular surfaces
- Removal without breaking

echnical information:	Properties	Spec.	Tolerance	Test Method
	Total Weight Total Thickness MD Tensile strength MD Elongation at break Adhesion to steel plate Temperature resistance	92 g/m² 125 μm > 28 N/cm > 8 % > 2,2 N/cm 90 °C (60 min), 11	± 8 % ± 10 %	ISO 536 AFERA 5006 AFERA 5004 AFERA 5004 AFERA 5001
Available colour:	yellow			
Storage details:	 We recommend a storage temperature between 15 and 25 °C The product should not be directly exposed to heat or humidity The product should be conditioned to room temperature before use 			
Shelf life:	12 months when stored in original carton at 23 °C and max. 50 % relative humidity			
Remark:	Above figures are for reference and cannot be treated as warranties. Customers are advised to test the material to determine the suitability against intended applications			

IMPORTANT NOTICE TO PURCHASER

All statements technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed and the following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential, arising out of the use of or the inability to use the product. Before using, users shall determine the suitability of the product for their intended use, and assume all risk and liability whatsoever in connection therewith. No statement or recommendation not contained herein shall have any force or effect unless in an agreement signed by officers of seller and manufacture.