

0220 Masking tape 90 °C



Tape structure:

Backing: saturated crepe paper

Adhesive: solvent borne rubber / resins adhesive

Characteristics:

Crepe paper masking tape with high performance, specific for automotive sector during collision repairs and painting processes with drying cycles at high temperatures up to 110 °C (for 30 min). It combines controlled unwinding, easy tear and conformability. Well performing in overlapping the tape, with masking paper and masking film, it provides excellent paint edges, clean and safe removal without residues and breakings.

Application fields:

automotive, aerospace, marine

Technical features:

multiple surfaces, no residual, high performance, all paints

Strengths:

- Resistance for 90 °C (60 min) 110 °C (30 min)
- Suitable for all paints
- High performances
- No residue
- Adaptable to irregular surfaces
- Removal without breaking

Technical information:

Properties	Spec.	Tolerance	Test Method
Total Weight	92 g/m ²	± 8 %	ISO 536
Total Thickness	125 µm	± 10 %	AFERA 5006
MD Tensile strength	> 28 N/cm		AFERA 5004
MD Elongation at break	> 8 %		AFERA 5004
Adhesion to steel plate	> 2,2 N/cm		AFERA 5001
Temperature resistance	90 °C (60 min), 110 °C (30 min)		

Available colour:

yellow

Storage details:

- We recommend a storage temperature between 15 and 25 °C
- The product should not be directly exposed to heat or humidity
- The product should be conditioned to room temperature before use

Shelf life:

12 months when stored in original carton at 23 °C and max. 50 % relative humidity

Remark:

Above figures are for reference and cannot be treated as warranties. Customers are advised to test the material to determine the suitability against intended applications

IMPORTANT NOTICE TO PURCHASER

All statements technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed and the following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential, arising out of the use of or the inability to use the product. Before using, users shall determine the suitability of the product for their intended use, and assume all risk and liability whatsoever in connection therewith. No statement or recommendation not contained herein shall have any force or effect unless in an agreement signed by officers of seller and manufacture.