

0181925 Cloth wireness tape


Description:

Cloth wireness tape

Adhesive:

Coated with solvent acrylic pressure-sensitive adhesive

Carrier:

Polyester

Application:

Used for wrapping automotive wire harness with high temperature resistance

Technical Details:

Properties	Value
Total thickness	0,25 ± 0,2 mm
Standard width	19 mm
Adhesion	4,9 N/cm
Tensile strength	148 N/mm
Tearing strength	40 N
Unwinding	6,5 N
Elongation	15 %
Temperature	40~ +125 °C

- Heat aging test: 125 °C/3000 h no crackle, no fading, no looseness.
Bending test no crazing and crackle appear.
- Low-temperature performance test: No crazing and crackle after 4 hours in -40 °C.
- Abrasion resistance: D grade (2580 m)
- Flame retardant: B grade flame retardant (10 s extinct away from fire)

Storage and shelf life:

Clean and dry in a well ventilated area, preferably at a temperature between 10 °C and 30 °C. Stored under these conditions shelf life will be a minimum of 12 months.

Remark:

Figures shown refer to average values only, based on tests carried out in conditioned laboratory and are not valid for specification. All information has to be intended as generic advise for the use of products. Users have to verify the suitability of each tape in actual application under specific condition.

IMPORTANT NOTICE TO PURCHASER

All statements technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed and the following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential, arising out of the use of or the inability to use the product. Before using, users shall determine the suitability of the product for their intended use, and assume all risk and liability whatsoever in connection therewith. No statement or recommendation not contained herein shall have any force or effect unless in an agreement signed by officers of seller and manufacture.