

## 03607 Double-sided PVC tape



### Construction:



Modified Solvent base Acrylic Adhesive  
 White UPVC, 0.100 mm  
 Modified Solvent base Acrylic Adhesive  
 Brown silicone liner 90 g/m<sup>2</sup>

### Description:

- \* untearable PVC filmic backing
- \* high initial adhesion (tack)
- \* very strong final bond
- \* high adhesion to critical, low-polar material like PP and PE
- \* excellent resistance against environmental and influences like light, humidity and solvent

### Technical Characteristics:

Test Standard	China GB	ASTM	FINAT	JIS
<b>Tape Thickness, mm</b>			0.230	
<b>Colour *</b>			White	
<b>Adhesion</b>	30 N/25 mm	30 N/25 mm	30 N/25 mm	30 N/25 mm
<b>Initial Tack</b>	15 # (ball)	3 cm	16 N/25 mm	15 # (ball)
<b>Holding Power</b>	> 100 hours	> 100 hours	> 100 hours	> 100 hours

(\*Color: can be black, red...)

### Applications:

Offer a very strong permanent bond, even on rough surfaces, and can be largely resistant to plasticizers. Bonding car mirrors, or moldings and decorative trim parts in plastic housings (furniture industry).

### Temperature:

Application (Minimum): 10 °C  
 Service (long term): -20 °C to 80 °C  
 Short term: 100 °C

### Available sizes:

6 mm x 50 m; 9 mm x 50 m; 12 mm x 50 m; 25 mm x 50 m

### Surface Preparation:

It is essential, as with all pressure sensitive tapes, that the surface to which the tape is applied be clean, dry and free of grease and oil.

### Storage and Shelf Life:

The shelf life of the products is one years when stored at 18-25 °C, 30-70 % relative humidity and out of direct sunlight, in good packaging.

### IMPORTANT NOTICE TO PURCHASER

All statements technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed and the following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential, arising out of the use of or the inability to use the product. Before using, users shall determine the suitability of the product for their intended use, and assume all risk and liability whatsoever in connection therewith. No statement or recommendation not contained herein shall have any force or effect unless in an agreement signed by officers of seller and manufacture.