

05538, 05560 BATHROOM BORDER TAPE

Tape structure:

Backing: Butyl Rubber

Product Description:

A self-adhesive butyl based decorative trim white caulk strip for bathroom fixture applications. Product pre-shaped for easy installation.

Features:

- Water & mildew resistance after full cure
- Flexible & crack resistant once cured
- Easy installation with pre-shaped feature
- Safe & low emission, suitable for indoor bathroom use

Main Application:

- Use to bridge small gaps in bathroom fixture applications, such as between fixture and floor or fixture and wall.



Technical information:

Properties	Typical result	Test method
Total Non-Volatile % Solids (Weight)	100%	Computrac Analyzer
Odor	Mild	Subjective
Pigment	Calcium Carbonate/TiO2	Known
Freeze/Thaw Stability	Passes 5 Cycles	Test Lab 0 °F/77 °F at 24 hrs or ASTM C731
Tack Free Time	8 hours	ASTM D2377
Full Cure	24 hours	Test Lab
Shore A Hardness	12	ASTM D2240
Application Temperature	15 °C to 33 °C	Test Lab
Toxicity	Non-toxic	Document Review
Stain Resistance	No Color Change	Test Lab
Water Resistance (full cure)	Excellent	Test Lab
Crack Resistance (full cure)	No crack	Test Lab
Peel Strength	8.8 N/cm	(Glass at 24 hr cure)
VOC Content	12%	Calculated
Mildew Resistance	Excellent (cured product)	Test Lab
Paintability	Excellent	Test Lab

Color:



SHELF LIFE AND STORAGE

Tapes should be used within 24 months when stored in original carton at 23 °C and max. 50 % relative humidity. We recommend a storage temperature between 15 and 25 °C. The product should not be directly exposed to heat or humidity. The product should be conditioned to room temperature before use

IMPORTANT NOTICE TO PURCHASER

All statements technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed and the following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential, arising out of the use of or the inability to use the product. Before using, users shall determine the suitability of the product for their intended use, and assume all risk and liability whatsoever in connection therewith. No statement or recommendation not contained herein shall have any force or effect unless in an agreement signed by officers of seller and manufacture. Customers are advised to test the material to determine the suitability against intended applications.