

## 05538, 05560 Bathroom tape



### Description:

A self-adhesive butyl based decorative trim white caulk strip for bathroom fixture applications. Product pre-shaped for easy installation.

### Application:

Use to bridge small gaps in bathroom fixture applications, such as between fixture and floor or fixture and wall.

### Technical Details:

Physical/Performance Property	Test Method	Typical Result
Total Non-Volatile % Solids (Weight)	Computrac Analyzer	100 %
Consistency/Appearance	Visual Observation	White Caulk Strip
Odor	Subjective	Mild
Base Polymer	Known	Butyl Rubber
Pigment	Known	Calcium Carbonate/TiO2
Freeze/Thaw Stability	Test Lab 0 °F/77 °F at 24 hrs or ASTM C731	Passes 5 Cycles
Shelf life	Lab 50 °C Oven – Accelerated	Minimum 2 years in original container at 25 °C
Tack Free Time	ASTM D2377	8 hours
Full Cure	Test Lab	24 hours
Shore A Hardness	ASTM D2240	12
Storage Conditions	Test Lab	5 °C to 33 °C
Application Temperature	Test Lab	15 °C to 33 °C
Toxicity	Document Review	Non-toxic when used as directed
Stain Resistance	Test Lab	No Color Change
Water Resistance (full cure)	Test Lab	Excellent
Crack Resistance (full cure)	Test Lab	No crack
Peel Strength (Glass at 24 hr cure)	Instron	5 lbs/inch
Clean up Solvent (before cure)	Test Lab	Mineral Spirits
Standard Packaging	Known	Plastic Clam Shell
VOC Content	Calculated	12 % by weight
Paintability	Test Lab	Excellent at Full Cure
Mildew Resistance	Test Lab	Excellent (cured product)

**Availability:** 38 mm x 3,35 m; 60 mm x 3,35 m

**Remark:** Above figures are for reference and cannot be treated as warranties. Customers are advised to test the material to determine the suitability against intended applications.

### IMPORTANT NOTICE TO PURCHASER

All statements technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed and the following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential, arising out of the use of or the inability to use the product. Before using, users shall determine the suitability of the product for their intended use, and assume all risk and liability whatsoever in connection therewith. No statement or recommendation not contained herein shall have any force or effect unless in an agreement signed by officers of seller and manufacture.