

0733 Acrylic Foam tape



Description:

0733 is clear acrylic tape. Due to its colorless tape is ideal for bonding transparent materials or for applications where a colored bond line is unacceptable.

Applications:

- Signage manufacturing
- Metal stiffener bonding
- Trim attachment
- Georgian bars
- Electronic parts

Product benefits:

- Service Temperature -30 °C to +80 °C (continuous)
- Temperature Short Term Performance Range -30 °C to +180 °C (maximum duration of 1 hour)
- Consisting of a high quality pressure sensitive acrylic adhesive
- Good resistance to moisture and plasticizer
- Very good Ultra violet light resistant
- Resistance to abrasion, corrosion and moisture
- Suitable for indoor and outdoor environments
- No known hazards associated with this products
- Pre-determined dimensional bonding tape reduces waste
- Clean to use

Technical properties:

Properties	Nominal value	Test Method
Total thickness (without liner)	1.0 mm	Scapa K1
90° Peel Adhesion (24 h)	60~70 N/25 mm	PSTC 2
Tensile strength	16~18 N/25 mm	PSTC 31
Elongation	950~1050 %	PSTC 31
Density	1000 kg/m ³	Scapa K2
Heat resistance (2.2 psi at 93 °C)	> 10 000 min	PSTC 7 mod.
Holding Power (4.4 psi at RT)	> 10 000 min	PSTC 7

Shelf life:

One year from date of shipment when stored in a cool dry place below 76 °F (24 °C). Rolls should be stored on end.

IMPORTANT NOTICE TO PURCHASER

All statements technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed and the following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential, arising out of the use of or the inability to use the product. Before using, users shall determine the suitability of the product for their intended use, and assume all risk and liability whatsoever in connection therewith. No statement or recommendation not contained herein shall have any force or effect unless in an agreement signed by officers of seller and manufacture.