

07439505 Reinforced Aluminum Butyl Rubber Tape

Description:

Provides instant airtight and waterproof perfectly bonded to various surfaces: aluminium steel, glass, wood, tiles, concrete, fiberglass, plastic and more. Product withstands all weather conditions, bonds and seals to any surface.

Structure:

- Anti-corrosive layer
- High purity aluminium
- High-density reinforcing net
- Nonwoven fabric
- Premium butyl rubber
- Liner



Typical physical properties:

Properties	Values	Test Method
Size	50mm x 5mm	
Total thickness (+/-10%)	- 1.0 mm	
Holding power minimum:		
Upper surface	>60	(JC/T942-2004 standard = ≥ 20)
Lower surface	>60	(JC/T942-2004 standard = ≥ 20)
Heat resistance	80°C, 2 hours	internal
Cold application	- 40°C	internal
Shear bonding strength	4.5 N/mm	JC/T942-2004 standard = ≥ 0.6
Peel strength (cement mortar bond)	1.2 N/mm	JC/T942-2004 standard = ≥ 0.6
Peel strength (steel plate)	1.2 N/mm	JC/T942-2004 standard = ≥ 0.6

Important note:

1. The data above are typical values only, and should not be used for specifications purpose
2. Tolerance: Weight and Thickness: ±10%; Width: ±3mm; Length: Cut Roll: ±0.3m, Jumbo Roll ±0.5%

Storage & shelf life:

12 months when stored at 21 °C (70 °F) / 50% relative humidity out of direct sunlight

IMPORTANT NOTICE TO PURCHASER

All statements technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed and the following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential, arising out of the use of or the inability to use the product. Before using, users shall determine the suitability of the product for their intended use, and assume all risk and liability whatsoever in connection therewith. No statement or recommendation not contained herein shall have any force or effect unless in an agreement signed by officers of seller and manufacture.